

PRODUCT DESCRIPTION: FIBFLOOR AS SL is a three component self-levelling epoxy resin based topping, which is laid at a thickness from 1 mm to 1.5 mm. It is a three component epoxy system with selected aggregates, epoxy resin and a hardener. FIBFLOOR AS SL provides a monolithic, smooth, non-porous, hygienic, chemical resistant floors which is easy to clean and maintain. It is available in a number of colors (see FIBREX SHADE CARD) and has sufficient strength to withstand industrial traffic of light, medium and heavy duty trolleys, fork lifts with nylon / rubber wheels. FIBFLOOR AS SL designed to achieve surface resistance in the Static Dissipative range 10^6 to 10^9 ohms.

AREAS OF APPLICATION

- Solar Industry
- Electronics & Electricals
- Chemical Factory
- Pharmaceuticals & Laboratory
- Automobiles & Engineering
- School & Educational Institutes
- Milk & Dairies
- Operation Theatres, Hospitals
- Industrial floors
- Operating rooms
- Laboratories
- Production and warehouses

Areas where sensitive electrical and electronic equipment are located, where there is a risk of explosion.

ADVANTAGE

- Solvent free
- Low viscosity
- Short waiting time
- Excellent bond strength
- High Mechanical Strength
- Easy mixing and applying
- Excellent Surface Resistivity
- Available in wide color range
- Excellent Adhesion Properties
- Long lasting anti-static properties
- Easily Cleanable & Low Maintenance

APPLICATION

SURFACE PREPARATION

- Prepare the surface by mechanical grinding or other suitable method.
- Remove dust, flakes, oil, grease or other loose foreign particles by sand blasting, iron brush or compressed air. Remove any old painting using a surface grinder.
- For best bond, concrete surface be prepared as per CSP 1, 2 or 3 before priming.
- Ensure that the new concrete is cured for at least 28 days and surface moisture content is below 4 % before application.

MIXING

- Add Component A to Component B (Hardener) of FIBFLOOR AS SL slowly to ensure complete dispersion and slowly add Component C (Filler) of FIBFLOOR AS SL to ensure complete dispersion. Mix for 5 - 10 minutes till a homogenous mix is obtained. The speed may be 300 - 500 rpm.

- Transfer this mix into a new container to avoid contamination of any unmixed Resin/Hardener. Then, wait for 2-3 minutes for the product to settle and allow the entrapped air to escape, before transferring the material onto the floor

PRIMING

- Prime concrete surface with FIBFLOOR AS PRIMER and allow it to dry for 6 – 8 hrs @ 27°C.

APPLICATION

- Apply mix of FIBFLOOR AS SL and spread evenly over the recommended area using a notch trowel of the appropriate notch size. The notch of the trowel should be double the desired thickness of the FIBFLOOR AS SL top coat.
- Anchor FIBFLOOR AS SL near walls, around columns / foundations and at edges of trenches / gutters / bays and expansion joints by cutting a groove of 3 mm, atleast 20 mm inside the border. Roll the spike roller with a long handle on applied FIBFLOOR AS SL to remove entrapped air. Ensure that the spike roller is not applied too long to leave any permanent indentation on surface and one should not use the spike roller after the topping has started to gel.
- Do not apply FIBFLOOR AS SL over untreated expansion joints. Treat expansion joints with **FIBSEAL PU 21/22** and use **Fibseal JSE 700 or Fibseal JSP 700** for treating control and construction joints.

CLEAN UP

- Clean all tools immediately after use with Fibrex Paint Remover. Do not allow material to harden.
- Service life of a floor will be considerably extended by good housekeeping. Regular cleaning may be carried out using a rotary scrubbing machine with a warm miscible cleaning agent at temperature up to 50° C.

TECHNICAL SPECIFICATIONS

Theoretical Coverage FIBFLOOR AS SL	1.6kg/m ² /mm & 2.4kg/m ² /1.5mm
Mix Density ASTM D 1475	1.70 ± 0.02 g / cc
Mixing ratio (A:B:C:D)	2.61:1:4.5:0.18 (by weight)

FIBFLOOR AS SL

3 Component Self Levelling Epoxy Floor Topping for anti-static system

Product # 114.15
Version no: 16.11.23

Tech Data

Pot Life @ 25° C	50 - 60 Minutes
Application Temperature	10 - 40° C
Curing Time @ 25° C	Foot Traffic 24 Hrs Vehicle Movement 72 Hrs Full Cure 7 Days
Shrinkage, After 7 Days Curing	Nil
Flexural Strength, After 7 Days Curing ASTM D 790	22 ± 2 MPa
Adhesion to Concrete, 7 Days Curing ASTM D 7234	> 3 MPa Concrete Failure
Surface Hardness, Shore D After 7 Days Curing ASTM D 2240	75 ± 5
Compressive Strength, After 7 Days Curing ASTM C 109	70 ± 5 MPa
Abrasion Resistance (1000 g), After 7 Days Curing ASTM D 4060	55 ± 5 mg / 1000 Cycle
Water Absorption ASTM D 570	< 0.5 %
Tensile Strength, After 7 days of curing ASTM D 882	12 ± 2 MPa

CHEMICAL RESISTANCE

Chemicals	Result
Water	Pass
Vegetable Oil	Pass
Lube Oil	Pass
Diesel	Pass
Petrol	Pass
Kerosene	Pass
Xylene	Short Term
Milk	Pass
Citric Acid (15%)	Pass
Sodium Hydroxide (50%)	Pass
Salt	Pass
HCl (10%)	Short Term
H ₂ SO ₄ (40%)	Short Term
HNO ₃ (10%)	Short Term

LIMITATIONS

- Do not apply FIBFLOOR AS SL on surfaces known to, or likely to, suffer from rising dampness, potential osmosis problems or having relative humidity greater than 75 %. Consult fibrex before using FIBFLOOR AS SL in those areas.
- Do not apply FIBFLOOR AS SL to asphalt, weak or infirm concrete, unmodified sand-cement screeds, PVC tiles or sheets, or substrates known to move substantially e.g. steel walkways.
- Do not apply FIBFLOOR AS SL over treated expansion joints.

- In common with all epoxy material, some light shades may fade in the long term, when placed in adverse exposed conditions. Such changes (discoloration) if any, are normal and has no effect on the performance of FIBFLOOR AS SL.

Please contact FIBREX for installation of floor coating over

- Oil / Fat rigged floors
- Floors with moisture content over 4 %
- Floors with rising moisture problem
- Asphalt based floor (interior)
- Floors with a pull off strength less than 1.5 N / mm²

PACKAGING

FIBFLOOR AS SL (A+B+C+D: 17.376 KG PACK)

1 Pack Cover 10.86m²@1.6 kg/m²/mm &

7.24m²@2.4kg/m²/1.5mm

Supply

2 Packs Set: 34.752 KG (A Part : 2 Nos, B Part : 2 Nos, C Part : 2 Nos & D Part : 2 Nos)

STORAGE

Store the material at temperatures between + 10° C and + 35° C. In originally sealed packages, the material can be stored for twelve months. But before opening the drums, be assured that the temperature of the materials has the ambient temperature to avoid condensation. Open containers of material should be used quickly to avoid moisture contamination.

PRECAUTIONS

During mixing and application the following precautions should be observed: ensure adequate ventilation and avoid contact of the material with the eyes, nasal passages, mouth and unprotected skin. Avoid contact with the hands by wearing protective gloves and using, if necessary, a suitable barrier cream. In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice and after contact with the skin wash immediately with plenty of soap and water (do not use solvents). Prolonged contact with the skin should be avoided, especially where the user has an allergic reaction to resin-based materials. Always wear gloves and eye/face protection as necessary. Observe personal hygiene, particularly washing the hands after work has been completed or at any interruption whilst work is in progress. Care should be taken when removing gloves to avoid contaminating the insides. In case of accidents seek medical advice.

FIBFLOOR AS SL

3 Component Self Levelling Epoxy Floor Topping for anti-static system

Product # 114.15
Version no: 16.11.23

Tech Data

DISPOSAL / SPILLAGE

Spillage of the product should be absorbed onto sand or other inert material and transferred to a suitable disposable vessel. Disposal of such spillage or empty packaging should be in accordance with local waste disposal authority regulations.

NOTE

The information supplied in this datasheet is based upon extensive experience and is given in good faith in order to help you. Our company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

HEALTH AND SAFETY

This material is intended to be used by trained professionals with proper equipment's. The following safety measures are recommended:

- Wear protective gloves, clothing, goggles, hearing protection for noise reduction and hard hats for falling debris.
- Do not eat, drink or smoke while in active contact with these materials.
- Avoid skin contact.
- Wash hands thoroughly with soap and cool water.
- Never wash the skin with a solvent.
- Anyone experiencing difficulty breathing when working with these materials or showing an allergic reaction should seek fresh air immediately and consult a physician if symptoms persist.

DISCLAIMER

Fibrex Construction Chemicals products though are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Fibrex Construction Chemicals wishes to clarify that any advice, recommendation, specification or information is accurate and correct, though it cannot, at any time assume any liability either directly or indirectly arising from the use of its products. This is because it has no direct or constant control over where or how its products are applied, and whether or not in accordance with the advice specification, recommendation or information given by it.

FIBREX OTHER PRODUCTS – WE DO

